

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08K 5/20	A1	(11) International Publication Number: WO 98/14512 (43) International Publication Date: 9 April 1998 (09.04.98)
(21) International Application Number: PCT/US97/18375 (22) International Filing Date: 3 October 1997 (03.10.97) (30) Priority Data: 60/028,063 4 October 1996 (04.10.96) US (71) Applicant (for all designated States except US): E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): VOGEL, Randall, Allen [US/US]; 905 Newgate Lane, Wilmington, DE 19808 (US). HOH, George, L., K. [US/US]; 1404 Fresno Road, Wilmington, DE 19803 (US). SHEKHAR, Alok [US/US]; 10 Snowgoose Cove, Greensboro, NC 27455 (US). (74) Agent: BROWDER, Monte, R.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		(81) Designated States: CA, JP, US, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: IMPROVED ETHYLENE VINYL ACETATE COMPOSITIONS AND FILM AND METHODS RELATED THERETO (57) Abstract The present invention relates to film-forming compositions containing ethylene vinyl acetate copolymers with a vinyl acetate percentage that causes film-forming problems and processability problems and an alkylene bisoleamide which is used to enhance the film forming capabilities of these high VA content resins. The invention also relates to films prepared from these compositions and to coating compositions.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

TITLEIMPROVED ETHYLENE VINYL ACETATE COMPOSITIONS AND FILM
AND METHODS RELATED THERETOBACKGROUND OF THE INVENTION5 Field of the Invention

The present invention relates to certain polymeric blends containing olefinic bisoleamides such as EBO (N,N-ethyleneBisOleamide) and ethylene copolymers such as ethylene vinyl acetate (EVA). The composition provides enhanced film forming properties in the production of monolayer or multilayer film products.

10

Description of Related Art

Ethylene vinyl acetate copolymers (EVA) are known and have a wide variety of applications in the industrial arts. EVA copolymers find commercial use in flexible, heat sealable, functional, and decorative hot-melt and solvent-applied
15 coatings; as wax additives to impart toughness, flexibility, and adhesion; as blending resins to impart flexibility to brittle materials; and as a component of hot-melt and solvent-applied adhesives. It is also known that the vinyl acetate percentage in these copolymers can be varied and many such resins are sold under the trademark ELVAX® by E. I. du Pont de Nemours and Company. The present
20 inventors have found that the film forming properties and processibility of this resin can vary with increasing vinyl acetate percentage and that high vinyl acetate copolymers (e.g. greater than about 0% VA by weight) can cause film processing problems. In an effort to solve this problem for high VA content ethylene copolymers, the inventors have surprisingly found that the addition of EBO
25 improves film forming capability while minimizing negative effects on film properties such as clarity or other required physical parameters.

U.S. Pat. No. 4,510,281 describes the combination of EVA copolymers with certain oleamides to provide tack free pellets for industrial end uses. The oleamides and other esters described therein as additives improve the free-flowing
30 properties of the pellets by incorporating into the polymer material prior to

pelletization about 500-10,000 parts per million (ppm), especially 1000-5000 ppm, based on the polymer weight of an additive selected from the group consisting of N,N'-ethylenebisoleamide, N,N'-ethylenebiserucamide, N,N'-diolelyladipamide, and N,N'-dierucyladipamide. There is no specific teaching in this reference of the use of the compositions therein to produce a film or a film having processing advantages. There is, however, a general teaching relating to improvement of the handling and packaging throughput in actual production as a way to monitor good slip properties or antiblocking properties, especially for higher vinyl acetate content copolymers which could not be assessed by standard stick temperature tests.

There is no requirement in the present invention that the additive be incorporated into the ethylene copolymer resin before pelletization.

Grades of ELVAX® containing, for example, N, N-ethylenebisoleamide have been sold by E. I. du Pont de Nemours and Company for industrial applications but have not been sold or used as packaging grade or film-forming resins. Grades of ELVAX® resins not containing an additive of this nature have been sold into the packaging market.

U.S. Pat. No. 4,956,232 discloses the use of slip additives in multilayer polypropylene films. Slip additives which may be used in making the films disclosed in the 4,956,232 patent are those which are incompatible with polypropylene, i.e., those which bloom to the surface from the core and skin layers. Non-ionic surfactants, such as the amides and carboxylic acids, were of particularly interest in this patent disclosure. Amides which were preferred included amides of carboxylic acids having at least five carbon atoms, for example, behenamide, linolenamide, arachidamide, ricinol-amide, palmitamide, myristamide, linoleamide, lauramide, capramide, perlargonamide, caprylamide, oleamide, steramide, N,N'-ethylene bisoleamide, and the most preferred slip additive, erucamide. Carboxylic acids which were also described as useful included those having at least four carbon atoms, for example, butyric, caproic, caprylic, capric, lauric, lauroleic, myristic, myristoleic, pentadecanoic, palmitic, palmitoleic, margaric, stearic, oleic, linoleic, linolenic, ricinoleic, 2,3-dihydroxystearic, 12-hydroxystearic, behenic,

eleostearic, arachidic, 2-ecosenoic, 4-eicosadienoic, 2-docosenoic, 2-tetracosenoic, 2,4,6-tetracosatrienoic and the like.

The slip additive in the above patent disclosure was preferably dry blended together with the polypropylene resin of layer (B) or the heat-sealable resin of layer (A) and then melt mixed. Alternatively, the additive could be incorporated into a minor portion of the resin as a master batch to form a high concentration mix of the additive and the resin. This could then be diluted to the appropriate proportion by the addition of more resin. There is no teaching herein of the use of any of these additives with an EVA resin or film.

U.S. Pat. No. 4,517,242 discloses a combination of ethylene copolymer resins and lubricating agents such as ethylenebisoleamides in glass coating compositions.

U.S. Patent No. 3,879,330 discloses food wrap consisting of a vinylidene chloride polymer and a thermoplastic urethane polymer. The food wrap films of the invention can contain conventional additives such as lubricating additives, anti-blocking agents, anti-cling agents, and the like, all of which are known in the art. To illustrate, the food wrap films of the invention typically contain up to about 3 weight percent diatomaceous earth as an anti-blocking agent and up to about 2 weight percent of ethylenebisoleamide as a slip agent.

U.S. Pat. No. 5,468,444, describes the production of oriented thermoplastic films by blown-film extrusion. U.S. Pat. No. 5,453,209 discloses chemical metal and oil treating compositions and processes related thereto. U.S. Pat. No. 4,394,473 discloses polybutadiene bags and films. U.S. Pat. No. 3,645,822 discloses a method for providing multilayer films having improved slip properties. U.S. Pat. No. 5,468,444 discloses film-forming thermoplastic resins containing lubricants selected from aliphatic alcohol fatty acid esters obtained from an aliphatic alcohol having 1 to 12 carbon atoms, and preferably 1 to 6 carbon atoms, and a fatty acid having 10 to 22 carbon atoms, and preferably 12 to 18 carbon atoms, such as glycerol monooleate, glycerol di- or trioleate, glycerol triricinoleate, glycerol acetylricinoleate, methyl acetylricinoleate, ethyl

acetylricinoleate, butyl acetylricinoleate, propylene glycol oleate, propylene glycol laurate, pentaerythritol oleate, polyethylene glycol oleate, polypropylene glycol oleate, polyoxyethylene glycerol, polyoxypropylene glycerol, sorbitan oleate, sorbitan laurate, polyethylene glycol sorbitan oleate, and polyethylene glycol sorbitan laurate; polyalkylene ether polyols, such as polyethylene glycol and polypropylene glycol; sugar fatty acid esters, epoxidized soybean oil, polyoxyethylene alkylamine fatty acid esters, polyoxyethylene alkylphenyl ethers; higher fatty acid amides having 12 to 22 carbon atoms, such as oleamide, stearamide, and erucamide; ethylene-bis-stearamide, ethylene-bisoleamide, polyethylene wax, polypropylene wax, and liquid paraffin. Suitable nucleating agents include inorganic substances, such as talc and silica. Suitable tackifiers include castor oil derivatives, low-molecular viscous polybutylene, sorbitan higher fatty acid esters, terpene resins, and petroleum resin.

BRIEF SUMMARY OF THE INVENTION

The present invention relates to a polymeric film forming composition comprising an ethylene copolymer selected from an ethylene copolymer and an olefinic bisoleamide selected from an oleamide which affects film-forming properties of high ester content ethylene copolymer resins which heretofore have not produced film with the requisite physical properties. The present invention relates to a film-forming composition consisting essentially of an ethylene copolymer having a percentage of vinyl acetate monomer incorporated at 10% wt or higher relative to the ethylene, and an olefinic bisoleamide of the formula described herein wherein the oleamide additive is not required to be added to the composition prior to pelletization of the ethylene copolymer. The percentage of bisoleamide necessary to have the beneficial physical properties varies with the percentage of vinyl acetate in the film or extrusion coating and depends upon the thickness of the film or coating. Upon reading this disclosure, one of ordinary skill in the art can readily adjust the percentages accordingly.

The present invention also relates to a coating composition for extrusion coating comprising an ethylene copolymer having ethylene and an ester containing monomer (e.g. vinyl acetate or C1-C6 alkyl acrylate esters) and a bisoleamide of the formula described herein wherein the oleamide is not added to the composition
5 prior to pelletization. The bisoleamide may be added post-pelletization and pre-extrusion.

The present invention also comprises a film having a first layer wherein the layer contains a polymeric composition comprising an ethylene copolymer selected from a copolymer of ethylene and a vinyl ester including vinyl acetate and an
10 olefinic bisoleamide selected from a compound of the formula $R-C(O)-NHC_2H_4NHC(O)-R$ wherein R is selected from a C_4-C_{25} saturated or unsaturated hydrocarbon. The invention also comprises a film having a first layer which contains a polymeric composition comprising an ethylene copolymer selected from a copolymer of ethylene and a vinyl ester including vinyl acetate and an olefinic
15 bisoleamide selected from a compound of the formula $R-C(O)-NHC_2H_4NHC(O)-R$ wherein R is selected from a C_4-C_{25} saturated or unsaturated hydrocarbon and a second layer comprising an ethylene acid ionomer selected from copolymers of ethylene and acrylic acid or methacrylic acid which are neutralized with a metal hydroxide or salt wherein the metal includes sodium, magnesium, calcium, etc.
20 Such ionomers are sold under the trademark SURLYN® by E. I. du Pont de Nemours and Company. Any of the film or coating layers may also contain blends of, for example, polyethylene including linear low density polyethylene or ultra low density polyethylene. The relative percentages of the blends depends upon the operator's target parameters and economic or other considerations.

25 The present invention further relates to a method of enhancing the slip characteristics of ethylene vinyl acetate films comprising adding an additive selected from an olefinic bisoleamide of the formula $R-C(O)-NHC_2H_4NHC(O)-R$ wherein R is selected from a C_4-C_{25} saturated or unsaturated hydrocarbon to an ethylene vinyl acetate copolymer and producing the film. In particular, the
30 bisoleamide permits effective slitting of blown film having a high percentage of

vinyl acetate or other ester functionality wherein said film, absent the bisoleamide, would adhere or otherwise stick together to preclude or prevent effective slitting of the two-layer structure coming out of the blown-film pinch rollers. The invention also relates to a process for making a film comprising, (a) blending an
5 olefinic bisoleamide selected from an olefinic bisoleamide of the formula $R-C(O)-NHC_2H_4NHC(O)-R$ wherein R is selected from a C_4-C_{25} saturated or unsaturated hydrocarbon with an ethylene copolymer selected from copolymers having ethylene and an ester containing monomer including vinyl acetate to form a blend and (b) forming a film or extrusion coating from the blend having at least one layer.

10 The present invention improves the separation of film layers in blown film, both in the separation of the film "layflat" after the blown film stalk is pressed together or nipped which collapses the hollow film stalk upon itself or in subsequent separation of the layers of film on a film roll. In the former separation, the cylindrical hollow film stalk such as from a spiral blown film die, is flattened
15 and collapsed between two moving nip rolls which flatten and press the cylindrical hollow film stalk into a two layer "layflat" sandwich. This film tube is cut at the edges and separated into two film layers, each of which are rolled onto a core forming rolls of film. The layflat is difficult to separate into the separate film layers, especially as the vinyl acetate monomer concentration increases in the
20 ethylene copolymer resin that the film is made from. In the latter case of film layers on a roll, layers of film which have been wound onto a core or roll may be difficult to separate since the layers tend to stick together, again especially as the vinyl acetate monomer concentration increases in the ethylene copolymer resin that the film is made from. In both cases, the N,N'-ethylenebisoleamide surface effects
25 of reducing tackiness and improving film slip (increasing) properties occurs fast enough to allow separation of the film layers and therefore successful operation of these type processes.

The present invention also improves film cutting or slitting in film fabrication processes. The surface effects of the N,N'-ethylenebisoleamide on the
30 film occurs fast enough so that film cutting is often improved. Without the olefinic

bisoleamide, the device which cuts the film such as a sharp razor, often catches on the film due to its tacky nature and poor slip qualities and results in the film jumping off the cutter or stretching of the film. Due to the quick action of reducing film tackiness and improving slip properties, in line film cutting is significantly improved with less drag forces between the cutting device and the film.

DETAILED DESCRIPTION

As summarized above, the present invention relates to ethylene copolymeric film-forming compositions containing an additive selected from an olefinic bisoleamide. The additive surprisingly provides enhanced film forming properties to an ethylene copolymer having a percentage of vinyl acetate monomer incorporated at 10 wt % or higher without impacting in a negative manner other film parameters such as clarity.

It has now been discovered that the film-forming and processing properties of polymers selected from the group consisting of

- (a) copolymers of ethylene with an ester containing monomer such as vinyl acetate containing about 10-40 weight percent of vinyl acetate or ester containing monomer, or

- (b) terpolymers of ethylene with vinyl acetate and carbon monoxide containing about 20-40 weight percent of vinyl acetate and 3-12 weight percent of carbon monoxide

can be significantly improved by incorporating into the polymer material about 500-10,000 parts per million (ppm), especially 500-5000 ppm, based on the polymer weight of an additive selected from the group consisting of N,N'-ethylenebisoleamide, N,N'-ethylenebiserucamide, N,N'-diolelyladipamide, and N,N'-dierucyladipamide. For the purpose of this invention (the term "oleyl" means cis-9-octadecenyl, $C_8H_{17}CH=CH(CH_2)_7CH_2-$; and the term "erucyl" means cis-13-docosenyl, $C_{18}H_{33}CH=CH(CH_2)_{11}CH_2-$). This nomenclature is generally used in the trade, for example, for oleyl alcohol, oleylamine, and erucylamine.

Polymeric Film Forming Compositions

Ethylene Copolymers

- 5 The ethylene copolymers of the present invention are selected from
- (a) copolymers of ethylene with vinyl acetate containing about 10-40 weight percent of vinyl acetate, or
- (b) terpolymers of ethylene with vinyl acetate and carbon monoxide containing about 20-40 weight percent of vinyl acetate and 3-12 weight percent of carbon
- 10 monoxide. These copolymers are generally available under the trade names ELVAX® or ELVALOY® as sold by E. I. du Pont de Nemours and Company and are generally prepared from ethylene and various percentages of vinyl acetate and, if necessary, carbon monoxide; or
- (c) copolymers of ethylene with ester containing monomers selected from methyl
- 15 acrylate, butyl acrylate, isobutyl acrylate or terpolymers containing carbon monoxide.

The preferred ethylene copolymers are selected from ethylene vinyl acetate copolymers having a vinyl acetate percentage by weight relative to the ethylene in the range of 15-40 wt.%. The most preferred ethylene vinyl acetate copolymer utilized in the film forming composition is selected from 15-33 wt.% or as exemplified herein.

- 20 For the purpose of this invention, the term "vinyl acetate copolymer" includes both the dipolymers and the terpolymers of ethylene with vinyl acetate and with carbon monoxide. Most commercial EVA dipolymers contain about 2-55% by weight of vinyl acetate. Terpolymers of ethylene with vinyl acetate and with carbon monoxide may contain about 18-40 weight percent of vinyl acetate and 2-
- 25 12 weight percent of carbon monoxide. Dipolymers of ethylene with vinyl acetate are available, e.g., from E. I. du Pont de Nemours and Company, Wilmington, Delaware, under the trademark Elvax®; the terpolymers with carbon monoxide can be made according to the teachings of U.S. Pat. Nos. 2,495,286 to Brubaker and 3,780,140 to Hammer. As the vinyl acetate content of the copolymer increases,
- 30 the copolymer tends to become increasingly sticky in both film and pellet states.

As discussed above, while use of the bisoleamides for antiblocking purposes is known, however, high VA content EVA copolymers are generally not used to produce film. The present inventors have discovered that the EVA copolymers with between 10-40% VA content can produce film with good properties provided that an olefinic bisoleamide is present in the composition as a primary additive.

Primary Additives

The olefinic bisoleamides are generally selected from a compound of the formula:

10 R-C(O)-NHCH₂CH₂NHC(O)-R wherein R is selected from C₄-C₂₅ saturated or unsaturated hydrocarbon moieties. In particular, the olefinic bisoleamides are selected from the group consisting of N,N'-ethylenebisoleamide, N,N'-ethylenebiserucamide, N,N'-diolelyladipamide, and N,N'-dierucyladipamide. The amides of this invention can be added to the copolymers by any convenient
15 technique, for example, in the melt, as a dry powder below its melting temperature, or as a concentrate in the same or any compatible polymer. The additive is thoroughly blended with the polymer, which is then used to produce (via extrusion) the film or coating of the present invention.

The preferred olefinic bisoleamide is selected from N,N-ethyleneBisOleamide (EBO). N,N'-Ethylenebisoleamide is available commercially from Carstab Corp. in
20 Reading, Ohio, under the name "Advawax" 240; from Humko Sheffield Co., Memphis, Tennessee, under the name "Kemamide" W-20; and from Glyco Chemical Co., Greenwich, Connecticut under the name "Glycolube" VL. The commercial product has a melting range of 113°-118°C. It is recommended by its manufacturers as
25 processing lubricant and antiblocking agent for various polymers and copolymers, especially as a slip agent for films. Its recommended level for these uses is 0.5-2%. As discussed above, however, there is no recommended use known for processing this additive with high VA content resins for film. The other additives can be made by known methods from readily available materials. Thus, N,N'-ethylenebiserucamide is
30 made by heating 1,2-ethylenediamine with erucic acid, and the remaining two amides

are made by heating either adipic acid or its dimethyl ester with at least two equivalents of either oleylamine or erucylamine. The adipamide thus has the formula $\text{RNH-C(O)-(CH}_2)_4\text{-C(O)-NHR}$ where R is either the oleyl or the erucyl group.

The relative weight percentage of olefinic bisoleamide to the ethylene copolymer ranges from 200-10,000 ppm. As indicated above, the percentage of bisoleamide will vary depending upon other parameters including VA content and thickness of the film or coating. In an 18 wt.% VA film, 1,000-3,000 ppm is the preferred range. In a 12 wt.% VA film, 700 ppm provides good slitting properties.

10 Additional Excipients

Additional excipients which are normally added to film forming or extrusion coating compositions include antiblock agents, fillers and other excipients known to those of ordinary skill in the art. As stated above, these additional ingredients can include other polymers, etc., including polyethylenes or ethylene copolymer ionomers such as those ionomers sold under the trademark SURLYN® by E. I. DuPont de Nemours and Company in additional or adjacent layers.

The film forming composition is prepared by mixing the olefinic bisoleamide with the ethylene copolymer as described below in a blown film forming process.

20 Film

Blown Film forming process:

The vinyl acetate and ethylene copolymer resin, either containing the N, N'ethylene bis oleamide or mixed with pellets containing the N, N'ethylene bis oleamide component, is conveyed to the feedthroat of an extruder. The extruder heats the resin particles, melts them and plasticates the copolymer into a blended melt and then pumps this melted copolymer material into a spiral die. The molten polymer is then pulled and formed into a circumferential hollow thin film stalk around an enclosed gas pocket or gas pressurized volume. The cooling of the molten polymer film which occurs just exit of the circular thin slit die opening and in drawing it over this enclosed gas volume provides sufficient strength to the

polymer mass to pull and form or draw a hollow thin film stalk. This cylindrical thin film with the enclosed gas volume is at some point, collapsed between two counter rotating rolls pressing the cylindrical film together forming a two layer sandwich referred to as a layflat. The layflat is typically cut or slit on its edges
5 forming 2 plies of film which are still layered together. The 2 film plies of the layflat are usually separated into individual films and rolled onto a turning core forming a roll of film. (This invention allows improved cutting and separation of the 2 film layer layflat for EVA films with VA levels of 10-40% - due to its fast bloom and fast surface enhancing effects of reducing tackiness, sticking and COF
10 (coefficient of friction).

Variants to this process include not slitting or separating the film layflat in the film forming process. If the circular die opening is horizontal (versus vertical in typical "film blowing" processing), the molten polymer forming into a film is sometimes referred to as profile or tubing extrusion.

15

Coating operations:

The vinyl acetate and ethylene copolymer resin, either containing the N, N'ethylene bis oleamide or mixed with pellets containing the N, N'ethylene bis oleamide component, is conveyed to the feedthroat of an extruder. The extruder
20 heats the resin particles, melts them and plasticates the copolymer into a blended melt and then pumps this melted copolymer material into a coating die. The coating die distributes the molten polymer uniformly to a thin straight slit opening. Molten polymer flowing from the thin straight slit die forms a curtain or web which can coat a substrate moving beneath the slit opening. Just after the web contacts
25 the moving substrate, the molten polymer is cooled by nipping, pressing or contacting the coating against a cool roll. The coated substrate is usually cut to a desired width and rolled onto a core. With higher VA EVA copolymer coating resins, the coating can stick to the cooling roll just after the molten polymer is dropped onto the moving substrate resulting in processing problems such as
30 tearing the substrate and wrapping around the cooling roll. This invention

facilitates using higher VA EVA copolymers due to the faster blooming effect of the slip and enhanced release properties that occur in the short time span prior to contacting the cooling roll.

5 **EXAMPLES**

The following examples provide exemplary support for the claimed invention and should not be construed as limiting the claimed subject matter. The examples below clearly demonstrate that the olefinic additive and resultant ethylene copolymeric composition has good film forming and processing properties even at
10 significant vinyl acetate percentages (e.g. greater than about 10% and preferably greater than about 18%) and the additive greatly enhances the slip characteristics of ethylene vinyl acetate films which makes these films easier to handle and process and allows the film to run faster on film forming equipment. As demonstrated below, the films containing the olefinic additive and, for example, EVA can be
15 made as single layer or a multilayer films (coextruded or laminated).

Example 1-

A coextrusion was conducted of mostly two-layer films of SURLYN® 8240, a 2.8 MI sodium ionomer having a melting point of 90°C, a product
20 available from DuPont and a blend of ELVAX® 3182, a 3 MI ethylene-vinyl acetate resin having a vinyl acetate content of 28 wt.%, and XEP 23. XEP 23 is a concentrate composed of 95 wt.% of ELVAX® 3182, 2 wt.% N,N'-ethylene-bis-oleamide (#5), and 3 wt.% silica (in the form of diatomaceous earth). The EVA resin layer was made up of 75 wt.% of the 3182 resin and 25 wt.% of the XEP 23
25 resin. The use level of the N,N'-ethylene-bis-oleamide was thus 0.5 wt.% or 5,000 ppm of the additive in the resin, and the amount of silica was 7,500 ppm.

These coextrusions were carried out on a 2.5" (63.5mm) WELEX blown film extrusion line extruding the EVA layer, and a 1.5" (38.1 mm) Davis extruder was used for the ionomer layer. The thickness of the EVA containing layer may

range from .8 mil to 8 mil (.2-2 mm). The temperature profiles for the two extruders were as shown below:

<u>Extruder</u>	<u>Rear</u>	<u>Ctr. Rear</u>	<u>Center</u>	<u>Ctr. Frt.</u>	<u>Front</u>	<u>Head</u>	<u>Adap.</u>	<u>Die</u>
Welex	300	350	375	380	380	380	380	380
Davis	375	390	390	390	380	380	380	380

- 5 The films produced ranged in total thickness between 4.02 and 5.07 mils (1-1.25 mm), and the percentages of the outside ionomer layer thickness ranged from 19.6 to 48.6% of the total. All of the samples were prepared at a blow-up ratio of approximately 1.75:1 using an 810" diameter Gloucester die. The film take-off rate ranged from 15 to 47 feet/min (4.6-14.3 met/min). Chilled air of
- 10 approximately 50°F (10°C) temperature was fed to the air ring at a rate of 30 to 59 cu. ft./min (0.85-1.7 cu m/min). The tubular film from these extrusions could be readily opened by the time it reached the slit/rewinder.

Example 2-

- 15 A concentrate was made containing 5.0 wt.% N,N'-ethylene-bis-oleamide #5, 7.5 wt.% "Superfloss" silica, with the remainder being the carrier resin ELVAX® 3182 to form "VAX CE9746". The concentration of the additives was selected so that 10 wt.% of the concentrate could to added to 90 wt.% of the EVA resin, the additive concentrations being 2.5X of those in XEP 23 in Example 1
- 20 above. Three coextruded films were produced from the compositions described below. Number 1 film was 1.2 mils (0.03 mm) ionomer recipe outside and 4.8 mils (0.12 mm) EVA recipe inside. Number 2 film was 2.5 mils (0.06 mm) ionomer recipe outside and 2.5 mils (0.06 mm) EVA recipe inside. Number 3 film was 2.5 mils (0.06 mm) ionomer Recipe outside and 2.5 mils (0.06 mm) ionomer recipe
- 25 inside (COMPARATIVE).

The composition of the ionomer recipe used for the above layers was:

93 wt.% SURLYN® 8240; 2.0 wt.% CONPOL 13B (12.5 wt.% "Superfloss"
Silica in 9 wt.% methacrylic acid (MAA)-content EMAA resin, 10 MI; antiblock
concentrate); and 5 wt.% "Ampacet" 11200 (Commercial White Concentrate of 70
wt.% TiO₂ in ethylene-methyl acrylate copolymer carrier).

5

The composition of the EVA formulation used in the three films was:

85.5 wt.% ELVAX® 3182; 10.0 wt.% VAX CE9746 Slip/Antiblock Concentrate;
and 4.5 wt.% "Ampacet" 11200 White Concentrate.

10

The two coextruded films having an outside layer of ionomer formulation and an
inside layer of EVA formulation were successfully coextruded into gusseted film
tubing. The face dimension of the tubing was 16.5" in width (419 mm), and each
gusset was 5.5" (140 mm) deep. Samples of the tubing taken on arrival at the
wind-up position of the film extruder could be readily opened, showing the
effectiveness of the N,N'-ethylene-bis-oleamide at the use level of 5,000 ppm. The
EVA resin has a much greater tendency to block and self-adhere, unlike the
ionomer resin that requires only silica antiblock to give openability of the gusseted
tubing.

20

Example 3-

Five-layer film coextrusions were also conducted as described herein. A
Comparative concentrate additive composition and a concentrate formulation of
the invention were prepared and compared for film-forming effectiveness and
capability. The five layer film comprised a center layer of a blend of 80 wt.%
ethylene-vinyl alcohol copolymer and 20 wt.% of ELVAX® 3182. On each side
of the center layer was a layer of an adhesive resin; and the outermost layers were
composed of an ultralow density linear low density polyethylene (ULDPE)
composition containing ELVAX®, a color concentrate, and either a Comparative
formulation (i.e., without alkylene oleamide) or the film-forming composition of

30

the invention. The Comparative resin blend for the outermost layer was made up of ULDPE29.27 (30 wt.%); ELVAX® 3182 (51.2%); SB#1 (a composition of 20 wt.% silica, 3.5 wt.% stearamide, and 3.5 wt.% erucamide in a carrier resin of an 18 wt.% vinyl acetate content EVA resin having an MI of 2.5 g/10min (ELVAX®
5 3170) which gave 19,000 ppm of silica in the layer and 6,832 ppm of combined amides as slip additive); and color concentrate (9.8 %).

The composition of the invention which includes the additive alkylene bisoleamides includes or consists essentially of SB#2 (a composition comprising 5 wt.% N,N'-
10 ethylene bis oleamide, 7.5 wt.% "Superfloss" silica with the remainder being ELVAX® 3182). This concentrate was present in the outer layer formulation at 10 wt.%; color concentrate (7.5%); ELVAX® 3182 (52.5%); and ULDPE (30%). Thus the outer layers contained 7,500 ppm silica and 5,000 ppm N,N'-ethylene bisoleamide.

15

The films were prepared using standard film processing and manufacturing techniques for five layer films of this nature and under the same extrusion conditions. The laid flat film tubing from the comparative five layer film containing SB#1 could not be opened by the time it reached the wind-up. In contrast, the film
20 tubing containing SB#2 concentrate which actually had lesser amounts of both the silica antblock and the amide(s), could be opened readily.

The above examples demonstrate that the production of high VA content EVA films can be accomplished without impairment of physical properties by incorporating an alkylene bisoleamide of the invention into the film-forming
25 composition. This additive can also be added to any ethylene vinyl acetate copolymer resin grade used to produce film in place of other slip additives and at lower concentrations. The enhanced migration properties of the bisoleamides in and onto film surfaces also enhances slip properties. The film-forming enhancing additive of the invention is particularly suitable for high VA content ethylene vinyl
30 acetate resins used to produce film which traditionally have high coefficients of

friction (COF); tackiness and blocking properties which discourages the use of these resins in film production. The tacking and blocking tendencies are reduced by the addition of the recited additive which permits faster bloom rates and therefore improves and allows or enables film processing and production of these

5 high VA content copolymeric resins. The inventors also noticed that use of the invention reduced nip roll and winding blocking tendencies and improved knife-razor performance in the conversion to film. Comparative experiments conducted at 18% VA and at 25% VA in an ethylene vinyl acetate copolymer with similar weight loading of ADVAWAX 240 (N,N'-ethylene bisoleamide) versus ecrumamide

10 showed that the former excipient enhanced film forming properties of the high VA copolymers and compared more favorably to the comparative amide. Bubble stability increased; razor slitting improved (smoother and cleaner); less problem occurred in separating the web layflat-25%VA content EVA film with comparative amide could not be separated while the run containing ADVAWAX 240 could be

15 separated. These favorable results occurred even at 50% concentration levels relative to the amide.

WHAT IS CLAIMED IS:

1. A film-forming composition, comprising,
 - (a) an ethylene copolymer wherein the copolymer has ethylene and a monomer selected from an ester containing moiety; and
 - 5 (b) an alkylene bisoleamide of the formula:
 $R-C(O)-NHC_2H_4NHC(O)-R$ wherein R is selected from a C_4-C_{25} saturated or unsaturated hydrocarbon wherein the monomer, absent component (b), provides sticking properties to the film composition to preclude film formation or processability.
- 10 2. The composition according to Claim 1 wherein the ethylene copolymer is selected from ethylene vinyl acetate, ethylene C_1-C_6 alkyl acrylates or ethylene C_1-C_6 alkyl methacrylates.
- 15 3. The composition according to Claim 2 wherein the vinyl acetate wt. % ranges from about 10-40 wt. %.
- 20 4. The composition according to Claim 1 wherein component (b) is selected from N,N' -ethylene bisoleamide.
5. The composition according to Claim 4 wherein the bisoleamide is present in a concentration range relative to the total film-forming composition of between 200 and 10,000 ppm.
- 25 6. The composition according to Claim 5 wherein the concentration range is between 300 and 8,000 ppm.
7. A film comprising at least one layer wherein at least one layer consists essentially of (a) an ethylene vinyl acetate copolymer and (b) an alkylene

bisoleamide of the formula: $R-C(O)-NHC_2H_4NHC(O)-R$ wherein R is selected from a C_4-C_{25} saturated or unsaturated hydrocarbon.

8. A film according to Claim 7 wherein the vinyl acetate percentage in the ethylene vinyl acetate copolymer ranges from about 10-40 wt. %.

9. A film according to Claim 8 wherein the bisoleamide is selected from N,N'-ethylene bisoleamide.

10. A film having at least two layers wherein the first layer is selected from a layer having an ionomeric resin and the second layer is selected from a layer having (a) an ethylene vinyl acetate copolymer and (b) an alkylene bisoleamide of the formula: $R-C(O)-NHC_2H_4NHC(O)-R$ wherein R is selected from a C_4-C_{25} saturated or unsaturated hydrocarbon.

11. A film having at least one layer wherein the layer comprises (a) a polyethylene and a blend of (b) an ethylene vinyl acetate copolymer having a VA content of between about 10-40 wt.% and (c) an alkylene bisoleamide.

12. The film according to Claim 11 wherein the alkylene bisoleamide is selected from N,N'-ethylene bisoleamide.

13. A method of enhancing the film-forming or processing properties of an ethylene vinyl acetate copolymer having a vinyl acetate content of between about 10-40 wt.% comprising adding a slip additive selected from an alkylene bisoleamide to said copolymer to form a film-forming composition.

14. The method according to Claim 13 wherein the alkylene bisoleamide is selected from N,N'-ethylene bisoleamide.

15. A method according to Claim 14 wherein the additive provides a faster bloom rate sufficient to alter the surface of said film to permit film separation, film slitting or film release from a cooling or nip roll.

- 5 16. A coating composition, comprising,
 (a) an ethylene copolymer wherein the copolymer has ethylene and a monomer selected from an ester containing moiety; and
 (b) an alkylene bisoleamide of the formula:
 $R-C(O)-NHC_2H_4NHC(O)-R$ wherein R is selected from a C_4-C_{25} saturated
10 or unsaturated hydrocarbon wherein the monomer, absent component (b), provides sticking properties to the film composition to preclude film formation or processability.

17. The coating composition according to Claim 16 wherein the
15 ethylene copolymer is selected from ethylene vinyl acetate and the alkylene bisoleamide is selected from N, N'-ethylenebisoleamide.

18. A process for producing blown film or extrusion coating,
 comprising
20 (i) making a composition comprising,
 (a) an ethylene copolymer wherein the copolymer has ethylene and a monomer selected from an ester containing moiety; and
 (b) an alkylene bisoleamide of the formula:
 $R-C(O)-NHC_2H_4NHC(O)-R$ wherein R is selected from a C_4-C_{25} saturated or
25 unsaturated hydrocarbon wherein the monomer, absent component (b), provides sticking properties to the film composition to preclude film formation or processability;
 (ii) extruding said composition through an extruder at 130°C-260°C to form a molten polymeric blend;

(iii) cooling the polymeric blend through a cooling or nip roll to form an extrusion coating or blown film wherein the bisoleamide additive modifies the surface of the blown film or extrusion coating to permit separation of the film or extrusion coating from the cooling or nip roll and slitting of the film.

5

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US97/18375

A. CLASSIFICATION OF SUBJECT MATTER IPC(6) : C08K 5/20 US CL : 524/232 According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) U.S. : 524/232, 229, 230 Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 5,399,401 A (POWELL) 21 March 1995, columns 3-6.	1-18
Y	US 4,517,242 A (SINHA et al.) 14 May 1985, examples.	1-18
Y	US 4,510,281 A (SMITH) 09 April 1985, columns 3-6 and examples.	1-18
Y	GB 2,289,281 A (ELF ATOCHEM S.A.) 15 November 1995, pages 3-9.	1-18
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
* Special categories of cited documents:	*T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
A document defining the general state of the art which is not considered to be of particular relevance	*X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
B earlier document published on or after the international filing date	*Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*A*	document member of the same patent family
O document referring to an oral disclosure, use, exhibition or other means		
P document published prior to the international filing date but later than the priority date claimed		
Date of the actual completion of the international search 03 DECEMBER 1997	Date of mailing of the international search report 23 DEC 1997	
Name and mailing address of the ISA/US Commissioner of Patents and Trademarks Box PCT Washington, D.C. 20231 Facsimile No. (703) 305-3230	Authorized Officer JEFFREY T. SMITH Telephone No. (703) 305-2551	